

PORTUGE AMERICA

2 pcf 32.04 kg/m³

E.	ttec	tive	Da	te	(6/1	/1	0

PHYSICAL PROPERTIES		TEST METHOD	VALUES	USA UNITS	VALUES	METRIC UNITS	
Density - Nominal	ASTM D3575	2.00	lb/ft³	32.04	kg/m³		
Density Range	ASTM D3575	1.8 - 2.5		28.8 - 40.9			
Tensile Strength	ASTM D412	54.50	psi	375.76	kPa		
Elongation at Break	ASTM D412	237.00	%	237.00	%		
Tear Resistance	ASTM D624	12.90	lb/in	230.37	kg/m		
Hardness Shore OO	ASTM D2240	52.70	Shore OO	52.70	Shore OO		
Compressive Stress							
Compression Set	25% ½hr		Pending	%	Pending	%	
	25% 24hr	ASTM D3575	Pending		Pending		
	50% ½hr	Suffix B	35.28		35.28		
	50% 24hr		18.16		18.16		
Compressive Strength	10%	ASTM D3575 Suffix D	Pending	psi	Pending	kPa	
	25%		8.50		58.61		
	40%		Pending		Pending		
	50%		19.30		133.07		
Working Temperature Range		Internal Test	-40 to 212	°F	-40 to 100	°C	
Water Absorption 7 days		Internal Test	Pending	% Vol (max)	Pending	% Vol (max)	
Flammability	FMVSS 302	Pass		Pass			
Thermal Conductivity at 50	ASTM C177	Pending	W/mK	Pending	W/mK		
Thermal Stability (24 HRS	ASTMD3575	Pending	% of change	Pending	% of change		

DIMENSIONS (usable)					
LENGTH	WIDTH	THICKNESS			
72 in	48 in	3 & 4 in			
1828.8 mm	1219.2 mm	101.6 mm			

BUN MARKINGS (Example)

Bun ID (Hand written across one 48" end of bun) 11-8-126 (Batch Number) II (2 PCF)

ADDITIONAL ASPECTS

VIZION is a closed cell chemically crosslinked polyethylene foam in bun form.

MSDS sheets available

Standard Colors: Gray, Black Natural

 ${}^{\star} \textit{The information above on VIZION chemically crosslinked polyethylene foam is presented to the best of our knowledge.}$

*Data represents typical values measured on 0.4" thick specimen and should be considered as a guideline only.

*This product data sheet is effective (insert date) and supersedes all previously published data.

Vizion Chemically crosslinked polyethylene foam is manufactured by PXL Crosslinked Foam Corporation exclusively for Palziv North America.